

Audurra™ Premium Plus Masking Foil

MASKING

Description:

Good cutting ability and electrostatic adhesion of the Audurra™ Premium Plus Masking Foil (Polythene light-blue transparent) accelerate the work steps and are a prerequisite for safe and accurate covering. Due to its heat resistance up to 125°C it can be used with infrared dryers. Important: No staining due to residual moisture on the vehicle, no severance of paint and water. Thanks to its superior thickness the foil is extremely tear-resistant enabling masking tapes to be removed / repositioned if needed. 100% Made in Germany!



Available in:

Article number	Description	Dimension
D15420546	Audurra™ Premium Plus Masking foil	4 m x 150 m
D15420547	Audurra™ Premium Plus Masking foil	5 m x 120 m
D15420548	Audurra™ Premium Plus Masking foil	6 m x 80 m

Compatible with:

Article number	Article description	Packaging unit
D15352436	Audurra mobile dispenser for foil cartons	1 piece
D15352432	Audurra Foil Cutter	1 bundle = 5 pieces
D15419691	Audurra Magnetic Foil Cutter	1 bundle = 5 pieces



Audurra™ Premium Plus Masking Foil

MASKING

Properties:

Property	Value & measuring unit	Measuring method
Density	~ 1,068 g / cm ³	following DIN EN 1183
Thickness	16 µm	following GPA (Thickness-profile)
Elongation at break <i>machine direction</i>	>300 N / mm	following DIN 53363
Elongation at break <i>transverse direction</i>	>450 N / mm	following DIN 53363
Dart drop	>50 g	following ASTM 1709-91
Dimension and Design	4m x 150m / 5m x 120m / 6m x 80m	

Storage remarks:

Storage time is 12 months from delivery date. Keep storage temperature between + 20° C / ± 10° C and the relative humidity by 30 – 90%.

Storage in closed rooms. Avoid exposure to UV-radiation.

This technical information has been given to the best of our knowledge. The above mentioned standards are average values and no granted assurance of special properties. This statement is limited to the material, in the state as it leaves the manufacturer and does not include possible modifications by conversion and/or handling after dispatch.